

Filtration Media Material Specifications

Test	Method	Units	Result
Mass Per Unit Area	ASTM 5261	Standard (Metric)	Standard (Metric)
Grab Tensile MD	ASTM D-4632	oz/yd. (g/m)	11.0 (341.16)
Grab Tensile TD	ASTM D-4632	lbs (kg)	118 (53.5)
Elongation at Peak MD	ASTM D-4632	lbs (kg)	89 (40.4)
Elongation at Peak TD	ASTM D-4632	percent	131
Wide Width Tensile MD	ASTM D-4595	percent	172
Wide Width Tensile TD	ASTM D-4595	lbs/in (kg/cm)	33 (5.89)
Elongation at Break MD	ASTM D-4595	lbs/in (kg/cm)	23 (4.11)
Elongation at Break TD	ASTM D-4595	percent	110
Mullen Burst	ASTM D-3786	percent	156
Puncture Resistance	ASTM D-4833	lbs/sq.in (kg/cm ²)	214 (15)
Trapezoid Tear Strength MD	ASTM D-4533	lbs (kg)	72 (32.7)
Trapezoid Tear Strength TD	ASTM D-4533	lbs (kg)	64 (29)
Permittivity(Constant Head)	ASTM D-4491	lbs (kg)	45 (20.4)
		sec ⁻¹	2.02
Permeability	ASTM D-4491	cm/sec	0.72
Flow Rate	ASTM D-4491	gal/ft ² /min. (l/m ² /min.)	151 (6152)
Apparent Opening Size /	ASTM D-4751	microns	100
micron		U.S. Sieve	140/150
Hydrocarbon Capacity (nominal)		gal/yd ² (l/m ²)	0.70 (3.17)